SPECIFICATION CONTROL DRAWING

55PC0813

WIRE, RADIATION-CROSSLINKED, MODIFIED, ETFE-INSULATED, GENERAL PURPOSE. NORMAL AIRFRAME

Date 07-15-04

vision

D

This specification sheet forms a part of the latest issue of Raychem Specifiction 55PC.

CONDUCTOR - NICKEL-COATED COPPER

INSULATION-

RADIATION-CROSSLINKED, MODIFIED ETFE

CONSTRUCTION DETAILS											
		CONDUCTOR STRANDING (number x AWG)	CONDUCTOR DIAMETER (in.)			FINISHED WIRE					
PART NUMBER 1/	WIRE SIZE (AWG)					MAXIMUM	DIAMETER			WEIGHT	
			LOWER SPEC LIMIT	TARGET VALUE	UPPER SPEC LIMIT	RESISTANCE AT 20°C (ohms/1000ft.)	LOWER SPEC LIMIT	(in.) TARGET VALUE	UPPER SPEC LIMIT	(lbs/1 TARGET VALUE	000 ft.) UPPER SPEC LIMIT
55PC0813-26-*	26	19 x 38	.0175	.0183	.0191	42.2	.0366	.0385	.0404	1.55	1.70
55PC0813-24-*	24	19 x 36	.0225	.0233	.0241	25.9	.0416	.0435	.0454	2.18	2.34
55PC0813-22-*	22	19 x 34	.0285	.0293	.0301	16.0	.0476	.0495	.0514	3.12	3.30
55PC0813-20-*	20	19 x 32	.0365	.0375	.0385	9.77	.0561	.0580	.0599	4.64	4.85
55PC0813-18-*	18	19 x 30	.0452	.0464	.0476	6.10	.0659	.0680	.0701	6.94	7.27
55PC0813-16-*	16	19 x 29	.0514	.0527	.0538	4.76	.0737	.0760	.0783	8.80	9.17
55PC0813-14-*	14	19 x 27	.0644	.0659	.0674	3.00	.0896	.0920	.0944	13.50	13.99
55PC0813-12-*	12	37 x 28	.0825	.0845	.0865	1.98	.1076	.1105	.1134	20.45	21.08
55PC0813-10-*	10	37 x 26	.1050	.1070	.1090	1.24	.1290	.1330	.1370	31.73	32.78
55PC0813-8-*	8	133 x 29	.158	.163	.169	.694	.188	.196	.203	56.8	59.9
55PC0813-6-*	6	133 x 27	.198	.205	.212	.436	.233	.242	.251	89.7	94.7
55PC0813-4-*	4	133 x 25	.250	.260	.268	.275	.300	.311	.322	146.	154.
55PC0813-2-*	2	665 x 30	.320	.330	.340	.177	.370	.383	.397	227.	240.
55PC0813-0-*	0	1045 x 30	.395	.415	.425	.113	.449	.466	.483	343.	366.
55PC0813-00-*	00	1330 x 30	.440	.462	.475	.089	.505	.525	.545	450.	481.

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C
Maximum continuous conductor temperature
VOLTAGE RATING: 600 volts (rms) at sea level
COLOR: White preferred
CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour

IDENTIFICATION AND COLOR STRIPING DURABILITY: 125 cycles (250 strokes) (minimum), 500 g weight

INSULATION ELONGATION AND TENSILE STRENGTH:

Total Insulation,

Elongation, 50% (minimum)

Tensile Strength, 5000 lbf/in² (minimum)

INSULATION FLAWS:

Spark Test, 3.0 kV (rms)

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION THICKNESS: .010 in. (nominal) total insulation

SHRINKAGE: 230 ± 3°C for 1 hour, 0.125 in. (maximum) in 12 in. VOLTAGE WITHSTAND TEST (Post Environmental):

2500 volts (rms)

PART NUMBER:

The "*" in the part numbers above shall be replaced by

color code designators.

1/ Example: AWG 22, white: 55PC0813-22-9

ANIC 22 white with black strings FFDC0042 22

AWG 22, white with black stripe: 55PC0813-22-90

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

Page 1 of 1

TITLE

DIMENSIONS ARE IN INCHES AND, UNLESS OTHERWISE DESIGNATED, ARE NOMINAL

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297